



Kelken Construction Systems
 550 Hartle Street
 Suite C
 Sayreville, NJ 08872
 (732) 416-6730 FAX (732) 416-6733

US Metric Chart ASTM-A276 SS 304
34 KSI Yield 85 KSI Tensile

Anchor Diameter in. (mm)	Drill Diameter in. (mm)	Tensile Stress Area	Embed Depth in. (mm)	Yield lb (kn)	Tensile lb. (kn)	Shear lb. (kn)
1/2 (12.7)	5/8 (15.9)	0.142	4 1/4 (108)	4828 (21.4)	12070 (53.7)	6035 (26.8)
5/8 (15.9)	3/4 (19.1)	0.226	6 (152)	7684 (34.1)	19210 (85.4)	9605 (42.7)
3/4 (19.1)	7/8 (22.2)	0.334	6 1/2 (165)	11356 (50.4)	28390 (126.3)	14195 (63.1)
7/8 (22.2)	1 (25.4)	0.462	7 1/2 (169)	15708 (69.8)	39270 (174.6)	19635 (87.3)
1 (25.4)	1 1/8 (28.6)	0.606	8 1/2 (216)	20604 (91.5)	51510 (229.0)	25755 (114.5)
1 1/8 (28.6)	1 1/4 (31.8)	0.763	10 (245)	25942 (115.2)	64855 (288.4)	32427 (144.2)
1 1/4 (31.8)	1 3/8 (34.9)	0.969	12 (205)	32946 (146.3)	82365 (366.2)	41182 (183.1)
1 3/8 (34.9)	1 1/2 (38.1)	1.155	15 (381)	39720 (174.4)	98175 (436.6)	49087 (218.3)
1 1/2 (38.1)	1 3/4 (44.4)	1.405	18 (457)	47770 (212.2)	119425 (531.1)	59712 (265.6)
1 3/4 (44.4)	2 (50.8)	1.900	20 (508)	64600 (286.9)	161500 (718.2)	80750 (359.1)
2 (50.8)	2 1/4 (57.2)	2.500	22 (559)	85000 (377.5)	212500 (945.0)	106250 (472.5)
2 1/4 (57.2)	2 1/2 (63.5)	3.250	26 (660)	110500 (490.8)	276250 (1228.5)	138125 (614.3)
2 1/2 (63.5)	2 3/4 (69.9)	4.000	30 (762)	136000 (604.0)	340000 (1512.0)	170000 (756.0)
2 3/4 (69.9)	3 (76.2)	4.930	34 (864)	167620 (744.4)	419050 (1863.5)	209525 (931.8)
3 (76.2)	3 1/4 (82.5)	5.970	40 (1016)	202980 (901.5)	507450 (2256.7)	253725 (1128.3)

Steel Strength ASTM A276-304 SS Annealed
 Yield = $F_y \times$ Tensile Stress Area
 Tensile = $F_t \times$ Tensile Stress Area
 Shear = $.50 \times$ Ultimate Steel Strength

Based on 3500 psi or greater compressive strength concrete 28 days old.

All values based on properly installed KeligrouT/KeligrouT 101-p per Technical Data Sheets